

PRODUCT DATA SHEET

CHARME VELVET

Pearlescent compact spatula decorative product



FEATURES

Interior decoration which, thanks to its pearlescent pigments and special fillers, gives the substrate a rustic finish with a changeable and pleasant play of light and reflected colours; suitable for obtaining special decorations with a textured and rough-touch effect.

Its high quality ensures maximum protection with an excellent finish and provides a hard, elastic and tenacious film with high resistance to the penetration of stains and dirt.

Being odourless, it is particularly suitable for applications in poorly ventilated areas.

COMPOSITION

Based on acrylic resins in water dispersion, selected aggregates and pearlescent pigments.

PROPERTIES OF THE PRODUCT

	VALUE	METHOD
DIFFUSION OF WATER VAPOUR	GOOD	
IMPACT RESISTANCE	EXCELLENT	
DIRT RETENTION	LOW	
WASH RESISTANCE (5 DAYS)	EXCELLENT	
SOLID BY WEIGHT	48-52 %	Internal PF25
DRYING TIME	Time for overcoating: 5-8h; Complete: 5 days	Internal PF2

SPECIFICATION DATA

	VALUE	METHOD
SPECIFIC WEIGHT	1270-1370 g/l	Internal PF3

SHELF LIFE

The product is stable 1 year if stored in the original can at temperature between +5 ° C and +30 ° C.

COLOUR RANGE

Silver. The range of colours can be extended in the shades in the relevant colour card. The colours can be produced with the Arreghini Colors 16 system. Between one production run and the next, the colour may be slightly different, so it is necessary to finish the job with the same production run.

TYPICAL USE

It is indicated to create a unique decorative effect in both public and private place where special decorative effects are desired. It is also possible to work on surfaces that are not perfectly smooth.

The Texture effect depends on the skills of the painter and the quantity applied on the surface, therefore the sample has an indicative value. It is advisable to previously prepare a sample in order to define the desired effect. To obtain a homogeneous surface, it is advisable to complete the finish work with the same tool and only one operator in a wet-on-wet processing with no interruption. Mix the product, using a mixer, 2 minutes before and after the introduction of the AC16 dyes.

Tools should be cleaned with water immediately after use.

TOOLS

Spatula, stainless steel trowel

THINNING

Up to 10% in volume with water

COVERAGE

7-10 m²/l per layer

**APPLICATION
TEMPERATURE**

+5 °C +30 °C

**COATING
SYSTEM**

On CLS, various, new or already painted, rough and irregular plasters, clean the surface to be decorated by removing any flaking parts and smooth with Jolli or Stuccocap. On wood apply the primer Opakite or Opakite W and sand the surface. On Iron supports apply a layer of Chromocap or Chromocap W.

On supports prepared as described above and on plasterboard

1. Apply a coat of Ecolora Absolutecap diluted 5-10% by volume with water using a short-haired roller.
2. After 3 hours, apply one or more coats of CHARME VELVET depending on the desired effect.

**SPECIFICATION
ITEM**

Acrylic paint in water dispersion for interiors suitable for metallic effect finishes, with high resistance to washing, to be applied in one or more layers, with an average consumption from 0.120 l/m² to 0.240 l/m² (one/two layers) on surfaces previously treated with a layer of *Ecolora Absolutecap*.

INSTRUCTIONS

To carry out the work in a workmanlike manner it is essential to follow the instructions for the preparation of the surface contained in the CAP Arreghini Books. The specification data was determined at +23 ° C with 65% relative humidity of the environment. Under different conditions, the data and times between one operation and another undergo changes. The technical information is intended as a guideline. Due to the enormous variety of surfaces and application conditions, it is recommended to check the suitability of the product and its effectiveness by tests carried out on place.