

**DESCRIPTION**

Wall primer formulated with water-dispersed synthetic resins, possessing a specific technology which generates a special film that ensures secure adhesion on different types of substrates as well as insulating and consolidating capacities.

It guarantees even absorption and hence a uniform finish and excellent adhesion for subsequent coats.

Thanks to the resin and special lamellar pigments contained in the product, Murisol W guarantees high breathability, better colour resistance and fewer coats during the painting cycle.

The product guarantees high vapor permeability and resistance to alkaline substrates.

**PROPERTY OF THE PRODUCT**

Coverage	GOOD
Adhesion to substrates in building	EXCELLENT
Water vapour permeability	EXCELLENT

**Method****SPECIFICATION DATA**

Coverage	80-90
Specific weight	1350-1450 g/l
Drying time	recoatable 5-8h; fully 24h

**Method**

PF11  
PF3  
PF2

**SHELF LIFE**

1 year minimum, stored in its unopened original can at temperatures between +5°C and +30°C.

**COLOUR RANGE**

White. The range may be extended to the colours of the *Tucano*, *Spazio 100* and *Area 115* sample books.

The colour could vary slightly from one production batch to the next; it is therefore important to finish the job with the same batch.

**TYPICAL USE**

Apply directly as a preventive coat on old paints, alkaline substrates such as plaster with different compositions (cement, common lime, pre-mixed, skim coat plaster for exterior insulation), concrete and fibrocement in one coat. Can be recoated with acrylic finishes, either elastomeric or siloxanic finishes such as products of lines *k81* and *Fasadecap*.

**TOOLS**

Roller, Brush, Spray.

**THINNING**

30-40% by volume with water

**COVERAGE**

8-10 m<sup>2</sup>/l per coat.

**APPLY**

+5°C +30°C

**SPECIFICATION ITEM**

Pigmented consolidating undercoat containing water dispersed resins featuring the *Eliokem* technology to be applied directly as a preventive coat on old paints, alkaline substrates such as plaster with different compositions (cement, common lime, pre-mixed, skim coat plaster for exterior insulation), concrete and fibrocement in one coat, at an average consumption rate of 110 ml/m<sup>2</sup>. Compatible with both acrylic and siloxanic water-based paints.

**INSTRUCTIONS**

To carry out the work in a proper way, it is needed to strictly follow the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical

information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary.